









| QUALITY CHARACTERISTICS | NORM | STANDARDS | RESULT |
|---|-----------------|--|-----------------------------------|
|  Water absorption of the body | ISO 10545-3 | ISO 10545-3 | 0.5% < E <= 3% (Bib) |
|  Breaking strength | ISO 10545-4 | ISO 10545-4 | >30N/mm ² |
|  Abrasion resistance | ISO 10545-7 | | Class 0 |
|  Frost resistance | ISO 10545-12 | ISO 10545-12 | Complies |
|  Chemical resistance | ISO 10545-13 | Household Chemicals Acids (Low Concentration) | GA (no effect) GLA (no effect) |
|  Thermal shock resistance | ISO 10545-9 | ISO 10545-9 | Complies |
|  Dynamic coefficient of friction | BOT 3000E | Not Applicable; Wall Tile Only | |
|  Slight Variation | See Below | Moderate Variation | V3 |



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

FOR THE BEST PRODUCT LAYING RESULTS, MATERIAL FROM AT LEAST THREE BOXES SHOULD BE MIXED

