









# CLEAN SLATE NATURAL

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	Eb ≤ 0.5%	Eb ≤ 0.02%
 <b>Breaking strength</b>	ISO 10545-4	> 35N/mm <sup>2</sup>	≥ 38N/mm <sup>2</sup>
 <b>Abrasion resistance</b>	ISO 10545-7		
 <b>Frost resistance</b>	ISO 10545-12	EN ISO 10545-12	Conforms
 <b>Chemical resistance</b>	ISO 10545-13	ASTM C650	GL; GA, GLA
 <b>Thermal shock resistance</b>	ISO 10545-9	EN ISO 10545-9	Conforms
 <b>Dynamic coefficient of friction</b>	BOT 3000E	DCOF Section 9.6	0.42
 <b>Variation</b>	See Below		V4



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

*For the best product laying results, material from at least three boxes should be mixed.*



[www.bfceramics.com](http://www.bfceramics.com)